


## WHAT IS CLAIMED IS:

1. A cosmetic composition comprising, in a cosmetically acceptable medium, at least one non-cellulose thickener and at least one aqueous emulsion comprising at least one silicone copolymer with a dynamic viscosity ranging from  $1 \times 10^6$  to  $100 \times 10^6$  cP, resulting from the addition reaction, in the presence of a catalyst, of at least:

- (a) one polysiloxane of formula (I):



in which:

- $\text{R}_1$ , which may be identical or different, are independently chosen from groups that can react by chain addition reaction,
- $\text{R}_2$  in formula (I), which may be identical or different, are independently chosen from alkyl, alkenyl, cycloalkyl, aryl, hydroxyl, and alkylaryl groups, and can optionally further comprise functional groups,
- $n$  is an integer wherein the polysiloxane of formula (I) has a kinematic viscosity ranging from 1 to  $1 \times 10^6$  mm<sup>2</sup>/s; and
- (b) at least one silicone compound comprising at least one and not more than two groups capable of reacting with the groups  $\text{R}_1$  of the polysiloxane (a), wherein:

- at least one of the compounds of type (a) and (b) comprises an aliphatic group ~~comprising an ethylenic unsaturation.~~

2. A composition according to claim 1, wherein  $R_1$  is chosen from a hydrogen atom and aliphatic groups comprising an ethylenic unsaturation.

3. A composition according to claim 2, wherein the aliphatic groups comprising an ethylenic unsaturation are chosen from vinyl, allyl and hexenyl groups.

*Page 37*  
4. A composition according to claim 1, wherein the groups  $R_2$  are chosen from hydroxyl groups; alkyl groups comprising from 1 to 20 carbon atoms; cycloalkyl groups comprising from 5 to 6 carbon atoms; phenyl groups; alkylaryl groups comprising from 7 to 20 carbon atoms; and can optionally further comprise functional groups chosen from ethers, amines, carboxyls, hydroxyls, thiols, esters, sulfonates and sulfates.

→ 5. A composition according to claim 1, wherein said alkenyl groups are chosen from alkenyl groups comprising from 2 to 10 carbon atoms.

6. A composition according to claim 1, wherein  $R_2$  is a methyl group.

7. A composition according to claim 1, wherein  $n$  is an integer ranging from 5 to 5,000.

*Page 38*  
8. A composition according to claim 1, wherein the compound of type (b) is another polysiloxane of type (a) in which at least one and not more than two groups  $R_1$  of the polysiloxane (b) can react with the groups  $R_1$  of the polysiloxane (a).

9. A composition according to claim 1, wherein, in the presence of a hydrosilylation catalyst, the at least one silicone copolymer is obtained by addition reaction of at least:

- (a) one  $\alpha,\omega$ -divinylpolydimethylsiloxane, and
- (b) one  $\alpha,\omega$ -dihydrogenopolydimethylsiloxane.

10. A composition according to claim 9, wherein the hydrosilylation catalyst is a platinum catalyst.

11. A composition according to claim 1, wherein said aqueous emulsion of the at least one silicone copolymer has a silicone droplet or particle size ranging from 10 nm to 50  $\mu\text{m}$ .

12. A composition according to claim 11, wherein said emulsion of the at least one silicone copolymer has a silicone droplet or particle size ranging from 0.3  $\mu\text{m}$  to 20  $\mu\text{m}$ .

13. A composition according to claim 1, wherein said aqueous emulsion of the at least one silicone copolymer represents from 0.5% to 15% by weight relative to the total weight of the composition.

14. A composition according to claim 1, wherein the at least one silicone copolymer is essentially non-crosslinked.

15. A composition according to claim 1, wherein the at least one silicone copolymer is present in an amount ranging from 0.05% to 10% by weight relative to the total weight of the composition.

16. A composition according to claim 15, wherein the at least one silicone copolymer is present in an amount ranging from 0.1% to 5% by weight relative to the total weight of the composition.

17. A composition according to claim 1, wherein said at least one non-cellulose thickener is chosen from natural thickeners and synthetic origin thickeners.

18. A composition according to claim 17, wherein said at least one non-cellulose thickener of natural origin is optionally chemically-modified and is chosen from xanthan gum, scleroglucan gum, gellan gum, rhamsan gum, alginates, maltodextrin, starch, starch derivatives, karaya gum, carob flour, and guar gums.

19. A composition according to claim 17, wherein said at least one non-cellulose thickener of synthetic origin is chosen from acrylic acid polymers, methacrylic acid polymers and copolymers obtained from at least one monomer chosen from acrylic acid and methacrylic acid.

20. A composition according to claim 19, wherein said at least one non-cellulose thickener of synthetic origin is chosen from acrylic acid/ethyl acrylate copolymers.

21. A composition according to claim 17, wherein said at least one non-cellulose thickener of synthetic origin is chosen from carboxyvinyl polymers.

22. A composition according to claim 19, wherein said at least one non-cellulose thickener of synthetic origin is chosen from copolymers of acrylamide and an acrylamide derivative.

23. A composition according to claim 1, wherein said at least one non-cellulose thickener is chosen from:

- crosslinked 2-acrylamido-2-methylpropanesulfonic homopolymers,
- optionally crosslinked copolymers of acrylamide and of ammonium acrylate,
- optionally crosslinked copolymers of acrylamide and of methacrylamide and of methacryloyloxyethyltrimethylammonium chloride, and

24. A composition according to claim 17, wherein said at least one non-cellulose thickener of synthetic origin is chosen from polyethylene glycols and polyethylene glycol derivatives.

26. A composition according to claim 25, wherein said optionally crosslinked copolymers of acrylamide and of ammonium acrylate are chosen from acrylamide/ammonium acrylate copolymers (5/95 by weight) crosslinked with a crosslinking agent comprising polyolefinic unsaturation.

28. A composition according to claim 27, wherein said allyl ethers of alcohols of the sugar series are chosen from erythritol, pentaerythritol, arabitol, mannitol, sorbitol and glucose.

32

30. A composition according to claim 29, wherein said neutralizing agent is chosen from sodium hydroxide, potassium hydroxide, aqueous ammonia and amines.

31. A composition according to claim 30, wherein said amines are chosen from triethanolamine and monoethanolamine.

32. A composition according to claim 23, wherein said crosslinked copolymers of acrylamide and of methacryloyloxyethyltrimethylammonium chloride are chosen from copolymers obtained by copolymerization of acrylamide and of dimethylaminoethyl methacrylate quaternized with methyl chloride, followed by crosslinking with a compound comprising olefinic unsaturation.

33. A composition according to claim 32, wherein said compound comprising olefinic unsaturation is chosen from methylenebisacrylamide.


34. A composition according to claim 17, wherein said at least one non-cellulose thickener is present in an amount ranging from 0.001% to 20% by weight relative to the total weight of the composition.

35. A composition according to claim 34, wherein said at least one non-cellulose thickener is present in an amount ranging from 0.01% to 10% by weight relative to the total weight of the composition.

36. A composition according to claim 35, wherein said at least one non-cellulose thickener is present in an amount ranging from 0.1% to 3% by weight relative to the total weight of the composition.

37. A composition according to claim 1 further comprising at least one cationic surfactant chosen from:


A) quaternary ammonium salts of formula (IV) below:



in which:

- the radicals  $R_1$ ,  $R_2$ ,  $R_3$ , and  $R_4$ , which may be identical or different, are independently chosen from linear and branched aliphatic radicals comprising from 1 to 30 carbon atoms, and aromatic radicals, wherein the aliphatic radicals optionally comprise hetero atoms, and
- $X^-$  is an anion chosen from the group of halides, phosphates, anions derived from organic acids,  $(C_2-C_6)$ alkyl sulfates, alkyl sulfonates, and alkylaryl sulfonates;

B) quaternary ammonium salts of imidazolinium of formula (V) below:




in which:

- $R_5$  is chosen from alkenyl and alkyl radicals comprising from 8 to 30 carbon atoms,
- $R_6$  is chosen from a hydrogen atom,  $C_1-C_4$  alkyl radicals, and alkenyl and alkyl radicals comprising from 8 to 30 carbon atoms,









in which:

- R<sub>15</sub> is chosen from C<sub>1</sub>-C<sub>6</sub> alkyl radicals and C<sub>1</sub>-C<sub>6</sub> hydroxyalkyl and C<sub>1</sub>-C<sub>6</sub> dihydroxyalkyl radicals;
- R<sub>16</sub> is chosen from:
  - acyl groups of the following formula:



wherein R<sub>19</sub> is defined below,

- linear and branched, saturated and unsaturated, C<sub>1</sub>-C<sub>22</sub> hydrocarbon-based radicals, and
- a hydrogen atom;
- R<sub>18</sub> is chosen from:
  - acyl groups of the following formula:



wherein  $\text{R}_{21}$  is defined below,

- linear and branched, saturated and unsaturated,  $\text{C}_1\text{-C}_6$

hydrocarbon-based radicals, and

- a hydrogen atom;

-  $\text{R}_{17}$ ,  $\text{R}_{19}$  and  $\text{R}_{21}$ , which may be identical or different, are independently

chosen from linear and branched, saturated and unsaturated,  $\text{C}_7\text{-C}_{21}$

hydrocarbon-based radicals;

- n, p and r, which may be identical or different, are independently integers

ranging from 2 to 6;

- y is an integer ranging from 1 to 10;

- x and z, which may be identical or different, are independently integers

ranging from 0 to 10; and

-  $\text{X}^-$  is chosen from simple and complex, organic and inorganic anions;

and

- provided that the sum  $x + y + z$  is from 1 to 15, and that when x is 0, then  $\text{R}_{16}$  is


chosen from linear and branched, saturated and unsaturated,  $\text{C}_1\text{-C}_{22}$

hydrocarbon-based radicals, and that when z is 0, then  $\text{R}_{18}$  is chosen from linear

and branched, saturated and unsaturated,  $\text{C}_1\text{-C}_6$  hydrocarbon-based radicals.

38. A composition according to claim 37, wherein said at least one cationic surfactant is chosen from:

A) quaternary ammonium salts of formula (IV) below:



wherein:

-  $X^-$  is an anion chosen from halides,  $(C_2-C_6)$ alkyl sulfates, phosphates, alkyl and alkylaryl sulfonates, and anions derived from organic acids, and

i) - the radicals  $R_1$ ,  $R_2$ , and  $R_3$ , which may be identical or different, are independently chosen from linear and branched aliphatic radicals comprising from 1 to 4 carbon atoms, optionally comprising hetero atoms, and aromatic radicals, and


-  $R_4$  is chosen from linear and branched alkyl radicals comprising from 16 to 30 carbon atoms;

ii) - the radicals  $R_1$  and  $R_2$ , which may be identical or different, are independently chosen from linear and branched aliphatic radicals comprising from 1 to 4 carbon atoms, optionally comprising hetero atoms, and aromatic radicals, and

-  $R_3$  and  $R_4$ , which may be identical or different, are independently chosen from linear and branched alkyl radicals comprising from 12 to 30 carbon atoms, wherein said radicals further comprise at least one function chosen from ester and amide functions.


39. A composition according to claim 37, wherein in said quaternary ammonium salts of formula (VII):

- $R_{15}$  is chosen from methyl and ethyl radicals,
- x and y are equal to 1;
- z is equal to 0 or 1;
- n, p and r are equal to 2;
- $R_{16}$  is chosen from:



wherein  $R_{19}$  is defined below,

- methyl, ethyl and  $C_{14}$ - $C_{22}$  hydrocarbon-based radicals, and
- a hydrogen atom;
- $R_{18}$  is chosen from:



- wherein  $R_{21}$  is defined below,

- a hydrogen atom; and
- $R_{17}$ ,  $R_{19}$  and  $R_{21}$ , which may be identical or different, are independently chosen from linear and branched, saturated and unsaturated,  $C_{13}$ - $C_{17}$  hydrocarbon-based radicals.

40. A composition according to claim 39, wherein  $R_{17}$ ,  $R_{19}$  and  $R_{21}$  are chosen from linear and branched, saturated and unsaturated  $C_{13}$ - $C_{17}$  aliphatic radicals.

41. A composition according to claim 39, wherein the hydrocarbon-based radicals are chosen from linear hydrocarbon-based radicals.

42. A composition according to claim 37, wherein the compounds of formula (VII) are chosen from diacyloxyethyldimethylammonium, diacyloxyethylhydroxyethylmethylammonium, monoacyloxyethyldihydroxyethylmethylammonium, triacyloxyethylmethylammonium and monoacyloxyethylhydroxyethyldimethylammonium salts.

43. A composition according to claim 42, wherein said monoacyloxyethylhydroxyethyldimethylammonium salts are chosen from monoacyloxyethylhydroxyethyldimethylammonium chloride salts and monoacyloxyethylhydroxyethyldimethylammonium methyl sulfate salts.

44. A composition according to claim 39, wherein when  $R_{16}$  and  $R_{18}$  are chosen from acyl radicals, said acyl radicals are obtained from plant oils chosen from palm oil and sunflower oil.

45. A composition according to claim 37, wherein  $X^-$  of said quaternary ammonium salts of formula (IV) is an anion chosen from chloride, bromide, iodide, methyl sulfate, acetate, and lactate.

46. A composition according to claim 37, wherein said aromatic radicals of said quaternary ammonium salts of formula (IV) are chosen from aryl and alkylaryl.

47. A composition according to claim 37, wherein said hetero atoms of said quaternary ammonium salts of formula (IV) are chosen from oxygen, nitrogen, sulfur

and halogens.

48. A composition according to claim 38, wherein said aliphatic radicals of formula (IV)(ii) are chosen from alkyl, alkoxy, alkylamide, polyoxy(C<sub>2</sub>-C<sub>6</sub>)alkylene, and hydroxyalkyl radicals comprising from 1 to 4 carbon atoms.

49. A composition according to claim 38, wherein said R<sub>3</sub> and R<sub>4</sub> of formula (IV)(ii) are chosen from (C<sub>12</sub>-C<sub>22</sub>)alkylamido(C<sub>2</sub>-C<sub>6</sub>)alkyl and (C<sub>12</sub>-C<sub>22</sub>)alkylacetate radicals.

50. A composition according to claim 37, wherein said R<sub>5</sub> of formula (V) is chosen from radicals derived from tallow fatty acid.

51. A composition according to claim 37, wherein in said quaternary ammonium salts of imidazolinium of formula (V):

- R<sub>5</sub> and R<sub>6</sub>, which may be identical or different, are independently chosen from alkenyl and alkyl radicals comprising from 12 to 21 carbon atoms,
- R<sub>7</sub> is methyl, and
- R<sub>8</sub> is hydrogen.

52. A composition according to claim 51, wherein said R<sub>5</sub> and R<sub>6</sub>, which may be identical or different, are independently chosen from radicals derived from tallow fatty acid.

53. A composition according to claim 37, wherein said diquaternary ammonium salts comprise propane tallow diammonium dichloride.

54. A composition according to claim 37, wherein said R<sub>15</sub> alkyl radicals of said quaternary ammonium salts of formula (VII) are chosen from linear and branched C<sub>1</sub>-C<sub>6</sub> alkyl radicals.

55. A composition according to claim 54, wherein said  $R_{15}$  radicals are linear radicals.

56. A composition according to claim 55, wherein said  $R_{15}$  radicals are chosen from methyl, ethyl, hydroxyethyl and dihydroxypropyl.

57. A composition according to claim 56, wherein said  $R_{15}$  radicals are chosen from methyl and ethyl.

58. A composition according to claim 37, wherein said sum of  $x + y + z$  of said quaternary ammonium salts of formula (VII) ranges from 1-10.

59. A composition according to claim 37, wherein said quaternary ammonium salts of formula (IV) are chosen from (a) compounds comprising at least two fatty aliphatic radicals comprising from 8 to 30 carbon atoms, (b) compounds comprising at least one fatty aliphatic radical comprising from 17 to 30 carbon atoms, and (c) compounds comprising at least one aromatic radical.

60. A composition according to claim 37, wherein said at least one cationic surfactant is chosen from behenyltrimethylammonium salts, stearamidopropyldimethyl(myristyl acetate)ammonium salts, Quaternium-27 and Quaternium-83.

61. A composition according to claim 37, wherein the at least one cationic surfactant is present in an amount ranging from 0.1% to 10% by weight relative to the total weight of the composition.

62. A composition according to claim 61, wherein the at least one cationic surfactant is present in an amount ranging from 0.5% to 7% by weight relative to the total weight of the composition.

63. A composition according to claim 62, wherein the at least one cationic surfactant is present in an amount ranging from 1% to 5% by weight relative to the total weight of the composition.

64. A composition according to claim 1 further comprising at least one surfactant chosen from anionic, nonionic, and amphoteric surfactants.

65. A composition according to claim 64, wherein the at least one surfactant chosen from anionic, nonionic, and amphoteric surfactants is present in an amount ranging from 0.1% to 60% by weight, relative to the total weight of the composition.

66. A composition according to claim 65, wherein the at least one surfactant chosen from anionic, nonionic, and amphoteric surfactants is present in an amount ranging from 3% to 40% by weight, relative to the total weight of the composition.

67. A composition according to claim 66, wherein the at least one surfactant chosen from anionic, nonionic, and amphoteric surfactants is present in an amount ranging from 5% to 30% by weight, relative to the total weight of the composition.

68. A composition according to claim 64, wherein the at least one surfactant chosen from anionic, nonionic, and amphoteric surfactants comprises at least one anionic surfactant salt chosen from alkyl sulfates, alkyl ether sulfates, alkylamidoether sulfates, alkylaryl polyether sulfates, monoglyceride sulfates; alkyl sulfonates, alkyl phosphates, alkylamide sulfonates, alkylaryl sulfonates,  $\alpha$ -olefin sulfonates, paraffin sulfonates; alkyl sulfosuccinates, alkyl ether sulfosuccinates, alkylamide sulfosuccinates; alkyl sulfosuccinamates; alkyl sulfoacetates; alkyl ether phosphates; acyl sarcosinates; acyl isethionates and N-acyltaurates.

69. A composition according to claim 64, wherein said at least one surfactant



is chosen from anionic surfactants chosen from alkaline salts, sodium salts, ammonium salts, amine salts, amino alcohol salts and magnesium salts.

70. A composition according to claim 68, wherein said alkyl and acyl portions of radicals of said salts comprise 1 and from 8 to 24 carbon atoms, and said aryl portions of radicals of said salts are phenyl.

71. A composition according to claim 64, wherein said at least one surfactant is chosen from anionic surfactants chosen from fatty acid salts, acyl lactates wherein the acyl radical comprises 8 to 20 carbon atoms, and weakly anionic surfactants.

72. A composition according to claim 71, wherein said fatty acid salts are chosen from the salts of oleic acid, ricinoleic acid, palmitic acid, stearic acid, coconut oil acid and hydrogenated coconut oil acid.

73. A composition according to claim 64, wherein said at least one surfactant is chosen from anionic surfactants chosen from alkyl-D-galactosiduronic acids and their salts, polyoxyalkylenated (C<sub>6</sub>-C<sub>24</sub>) alkyl ether carboxylic acids and their salts, polyoxyalkylenated (C<sub>6</sub>-C<sub>24</sub>) alkylaryl ether carboxylic acids and their salts, and polyoxyalkylenated (C<sub>6</sub>-C<sub>24</sub>) alkylamido ether carboxylic acids and their salts.

74. A composition according to claim 71, wherein said weakly anionic surfactants comprise from 2 to 50 ethylene oxide groups.

75. A composition according to claim 68, wherein said at least one anionic surfactant salt is chosen from alkyl sulfates and alkyl ether sulfates.

76. A composition according to claim 64, wherein said at least one surfactant is chosen from nonionic surfactants chosen from polyethoxylated, polypropoxylated and polyglycerolated fatty acids, alkylphenols,  $\alpha$ -diols and alcohols having a fatty aliphatic

chain comprising 8 to 18 carbon atoms, wherein the number of ethylene oxide and propylene oxide groups ranges from 2 to 50 and the number of glycerol groups ranges from 2 to 30, copolymers of ethylene oxide and of propylene oxide, condensates of ethylene oxide and of propylene oxide with fatty alcohols, polyethoxylated fatty amides comprising from 2 to 30 mol of ethylene oxide, polyglycerolated fatty amides comprising on average 1 to 5 glycerol groups, polyethoxylated fatty amines comprising from 2 to 30 mol of ethylene oxide, oxyethylenated fatty acid esters of sorbitan comprising from 2 to 30 mol of ethylene oxide, fatty acid esters of sucrose, fatty acid esters of polyethylene glycol, alkylpolyglycosides, N-alkylglucamine derivatives, and amine oxides.

77. A composition according to claim 76, wherein said polyglycerolated fatty amides comprise on average 1.5 to 4 glycerol groups.

78. A composition according to claim 76, wherein said amine oxides are chosen from (C<sub>10</sub>-C<sub>14</sub>)alkylamine oxides and N-acylaminopropylmorpholine oxides.


79. A composition according to claim 76, wherein said nonionic surfactants are chosen from alkylpolyglycosides.

80. A composition according to claim 64, wherein said at least one surfactant is chosen from amphoteric surfactants chosen from aliphatic secondary and tertiary amine derivatives wherein the aliphatic radical is chosen from linear and branched chain radicals comprising 8 to 22 carbon atoms and comprising at least one water-soluble anionic group, (C<sub>8</sub>-C<sub>20</sub>)alkylbetaines, sulfobetaines, (C<sub>8</sub>-C<sub>20</sub>)alkylamido(C<sub>1</sub>-C<sub>6</sub>)alkylbetaines, and (C<sub>8</sub>-C<sub>20</sub>)alkylamido(C<sub>1</sub>-C<sub>6</sub>)alkylsulfobetaines.

81. A composition according to claim 80, wherein said at least one water-

soluble anionic group is chosen from carboxylates, sulfonates, sulfates, phosphates and phosphonates.


82. A composition according to claim 80, wherein said amine derivatives are chosen from the compounds:



in which:

- $R_2$  is chosen from alkyl radicals derived from an acid  $R_2\text{-COOH}$  present in hydrolysed coconut oil, heptyl, nonyl and undecyl radicals,
- $R_3$  is chosen from  $\beta$ -hydroxyethyl groups, and
- $R_4$  is chosen from carboxymethyl groups;

and



in which:

- (B) is  $\text{-CH}_2\text{CH}_2\text{OX}'$ , with  $X'$  chosen from a  $\text{-CH}_2\text{CH}_2\text{-COOH}$  group and a hydrogen atom,
- (C) is  $\text{-(CH}_2)_z\text{-Y}'$ , with  $z = 1$  or  $2$ , and with  $Y'$  chosen from  $\text{-COOH}$  and  $\text{-CH}_2\text{-CHOH-SO}_3\text{H}$  radicals,
- $R_5$  is chosen from alkyl radicals and unsaturated  $C_{17}$  radicals.

83. A composition according to claim 82, wherein said alkyl radicals  $R_5$  are chosen from (a) alkyl radicals of an acid  $R_5\text{-COOH}$  present in oils chosen from coconut oil and hydrolysed linseed oil, and (b)  $C_{17}$  alkyl radicals and the iso forms.

84. A composition according to claim 82, wherein said alkyl radicals of said  $R_5$  are chosen from alkyl radicals chosen from  $C_7$ ,  $C_9$ ,  $C_{11}$  and  $C_{13}$  alkyl radicals.

85. A composition according to claim 64, wherein said at least one surfactant is chosen from at least two surfactants of different types.

86. A composition according to claim 85, wherein said at least two surfactants of different types are chosen from (a) more than one anionic surfactant, (b) at least one anionic surfactant and at least one amphoteric surfactant, and (c) at least one anionic surfactant and at least one nonionic surfactant.

87. A composition according to claim 64, wherein said at least one surfactant is chosen from anionic surfactants chosen from  $(C_{12}-C_{14})$ alkyl sulfates of sodium, of triethanolamine and of ammonium,  $(C_{12}-C_{14})$ alkyl ether sulfates of sodium, of triethanolamine and of ammonium, oxyethylenated with 2.2 mol of ethylene oxide, sodium cocoyl isethionate, and sodium  $(C_{14}-C_{16})$ - $\alpha$ -olefin sulfonate, and from an amphoteric surfactant chosen from either:

- amine derivatives comprising disodium cocoamphodipropionate and sodium cocoamphopropionate, or
- amphoteric surfactants of zwitterionic type.

88. A composition according to claim 87, wherein said amphoteric surfactants of zwitterionic type are chosen from alkylbetaines.

89. A composition according to claim 88, wherein said alkylbetaines are chosen from cocobetaine.


90. A composition according to claim 1 further comprising at least one additive chosen from fragrances, nacreous agents, preserving agents, silicone

sunscreens, non-silicone sunscreens, vitamins, provitamins, cationic, amphoteric, anionic and nonionic polymers, proteins, protein hydrolysates, 18-methyleicosanoic acid, hydroxy acids, panthenol, volatile and non-volatile, cyclic and linear and crosslinked, modified and non-modified silicones, ceramides, pseudoceramides, and plant, animal, mineral and synthetic oils.

91. A composition according to claim 90, wherein said at least one additive is present in an amount ranging from 0 to 20% by weight relative to the total weight of the composition.

92. A rinse-out conditioner, a leave-in conditioner, a composition for permanent-waving the hair, a composition for straightening the hair, a composition for dyeing the hair, a composition for bleaching the hair, a rinse-out composition to be applied before a procedure chosen from dyeing, bleaching, permanent-waving and straightening the hair, a rinse-out composition to be applied after a procedure chosen from dyeing, bleaching, permanent-waving and straightening the hair, a rinse-out composition to be applied between the two steps of a permanent-waving operation, a rinse-out composition to be applied between the two steps of a hair-straightening operation, a washing composition for the body, an aqueous lotion, an aqueous-alcoholic lotion, a gel, a milk, a cream, an emulsion, a thickened lotion, a mousse, or a detergent composition comprising a washing base comprising, in a cosmetically acceptable medium, at least one non-cellulose thickener and at least one aqueous emulsion comprising at least one silicone copolymer with a dynamic viscosity ranging from  $1 \times 10^6$  to  $100 \times 10^6$  cP, resulting from the addition reaction, in the presence of a catalyst, of at least:

- (a) one polysiloxane of formula (I):



in which:

- R<sub>1</sub>, which may be identical or different, are independently chosen from groups that can react by chain addition reaction,
- R<sub>2</sub> in formula (I), which may be identical or different, are independently chosen from alkyl, alkenyl, cycloalkyl, aryl, hydroxyl, and alkylaryl groups, and can optionally further comprise functional groups,
- n is an integer wherein the polysiloxane of formula (I) has a kinematic viscosity ranging from 1 to 1 x 10<sup>6</sup> mm<sup>2</sup>/s; and

- (b) at least one silicone compound comprising at least one and not more than two groups capable of reacting with the groups R<sub>1</sub> of the polysiloxane (a), wherein:


- at least one of the compounds of type (a) and (b) comprises an aliphatic group comprising an ethylenic unsaturation.

93. An aqueous or aqueous-alcoholic lotion according to claim 92, said lotion being suitable for skin care or for hair care.

100. A detergent composition comprising a washing base according to claim 99, wherein said washing base is present in an amount ranging from 8% to 25% by weight, relative to the total weight of the final composition.

101. A process of washing or caring for a keratin material comprising applying to said keratin material a composition comprising, in a cosmetically acceptable medium, at least one non-cellulose thickener and at least one aqueous emulsion comprising at least one silicone copolymer with a dynamic viscosity ranging from  $1 \times 10^6$  to  $100 \times 10^6$  cP, resulting from the addition reaction, in the presence of a catalyst, of at least:

- (a) one polysiloxane of formula (I):



in which:


- $\text{R}_1$ , which may be identical or different, are independently chosen from groups that can react by chain addition reaction,
- $\text{R}_2$  in formula (I), which may be identical or different, are independently chosen from alkyl, alkenyl, cycloalkyl, aryl, hydroxyl, and alkylaryl groups, and can optionally further comprise functional groups,
- $n$  is an integer wherein the polysiloxane of formula (I) has a kinematic viscosity ranging from 1 to  $1 \times 10^6$  mm<sup>2</sup>/s; and
- (b) at least one silicone compound comprising at least one and not more than two groups capable of reacting with the groups  $\text{R}_1$  of the polysiloxane (a), wherein:



- at least one of the compounds of type (a) and (b) comprises an aliphatic group comprising an ethylenic unsaturation.

102. A process for treating a keratin material comprising applying to said keratin material a composition comprising, in a cosmetically acceptable medium, at least one non-cellulose thickener and at least one aqueous emulsion comprising at least one silicone copolymer with a dynamic viscosity ranging from  $1 \times 10^6$  to  $100 \times 10^6$  cP, resulting from the addition reaction, in the presence of a catalyst, of at least:

- (a) one polysiloxane of formula (I):



in which:

- $\text{R}_1$ , which may be identical or different, are independently chosen from groups that can react by chain addition reaction,
- $\text{R}_2$  in formula (I), which may be identical or different, are independently chosen from alkyl, alkenyl, cycloalkyl, aryl, hydroxyl, and alkylaryl groups, and can optionally further comprise functional groups,
- $n$  is an integer wherein the polysiloxane of formula (I) has a kinematic viscosity ranging from 1 to  $1 \times 10^6$  mm<sup>2</sup>/s; and


- (b) at least one silicone compound comprising at least one and not more than two groups capable of reacting with the groups  $R_1$  of the polysiloxane (a), wherein:

- at least one of the compounds of type (a) and (b) comprises an aliphatic group comprising an ethylenic unsaturation,  
and optionally rinsing said composition out with water.

103. A process for washing or treating a keratin material according to claim 102, wherein said keratin material is chosen from hair, skin, eyelashes, eyebrows, nails, lips and scalp.

104. A process for manufacturing a cosmetic product comprising including in said product at least one non-cellulose thickener and at least one aqueous emulsion comprising at least one silicone copolymer with a dynamic viscosity ranging from  $1 \times 10^6$  to  $100 \times 10^6$  cP, resulting from the addition reaction, in the presence of a catalyst, of at least:

- (a) one polysiloxane of formula (I):



in which:

- $R_1$ , which may be identical or different, are independently chosen from groups that can react by chain addition reaction,
- $R_2$  in formula (I), which may be identical or different, are independently chosen from alkyl, alkenyl, cycloalkyl, aryl, hydroxyl, and alkylaryl groups, and can optionally further comprise functional groups,
- $n$  is an integer wherein the polysiloxane of formula (I) has a kinematic viscosity ranging from 1 to  $1 \times 10^6 \text{ mm}^2/\text{s}$ ; and
- (b) at least one silicone compound comprising at least one and not more than two groups capable of reacting with the groups  $R_1$  of the polysiloxane (a), wherein:
  - at least one of the compounds of type (a) and (b) comprises an aliphatic group comprising an ethylenic unsaturation.